

628 ARO-PLATE II SG: INTERIOR/EXTERIOR FIRE RETARDANT, QUICK DRY SEMI-GLOSS ENAMEL

CHARACTERISTICS

- NFPA Life Safety Code 101, Section 6-5.3 Interior Wall & Ceiling Finish, Class A Fire Retardant rating as tested by ASTM E-84.
- Top of the line commercial quality
- Quick drying interior / exterior synthetic semi-gloss enamel
- Excellent chemical resistance and abrasion resistance
- For metal or wood

PHYSICAL PROPERTIES

SOLIDS:

Solids by Weight..... 68%
Solids by Volume..... 53%

FINISH:

Gloss @ 60° 75-80

COLORS:

Available in a wide range of industrial colors, white, medium, deep, accent, neutral and raw umber bases.

VISCOSITY:

Package Viscosity.....84-91 KU

VOC:

Coating VOC.....347 gms/L
Material VOC..... 327 gms/L

Weights & Measurements.....±5%

PERFORMANCE PROPERTIES

COVERAGE:

Surface..... Sq.ft./GA*
Metal 300-400
Smooth Wood 300-400

*Approximate coverage for each coat.

DRYING TIME:

To Touch 1-2 hours
Dust Free 2-3 hours
Tack Free 4 hours
To Handle..... 8 hours
Dry Hard..... 8 hours
To Recoat (brush) Overnight
To Recoat (spray) 8hrs

NOTE: Drying times increase with temperatures below 50°F or relative humidity above 80%, *especially in darker colors.*

MIL THICKNESS:

Wet4.0
Dry2.0

PREPARATION & PRIMING

METAL:

Scrape, power tool clean and sand the surface to remove any dirt, dust, grease, loose shop prime, oil, rust, scale, and other contaminants. New metal should be chemically cleaned prior to priming with a solvent meeting local VOC regulations.

Prime with two coats of 561 Acrylic Metal Primer. Pretreat all galvanized or non-ferrous metal surfaces.

WOOD:

Patch all voids with the appropriate patching or caulking material. Clean the surface to remove any dirt, dust, grease, mildew, oil, wax, and other contaminants.

Prime with 367 Fraflo II (interior-alkyd) or 372 Exterior Wood Undercoater (exterior-alkyd).

PREVIOUSLY PAINTED SURFACES:

Patch all voids with the appropriate patching or caulking material. Wash, scrape, sand and clean the surface to remove any chalk, dirt, dust, grease, loose paint, mildew, oil, wax, and other contaminants.

Prime where necessary with the appropriate primer for the substrate.

APPLICATION

METHODS:

This product may be applied by brush, roller, or airless sprayer. Apply coating evenly while maintaining a "wet edge" to prevent lapping.

THINNING:

This product is designed to be used at package consistency. **DO NOT THIN.**

CLEAN-UP:

Clean tools, equipment, and work area with solvent meeting local VOC regulations.

NOTICE:

Alkyd-based paints will yellow. Some degree of yellowing is inevitable with this product and the lighter the color, the more noticeable the yellowing will be. Yellowing will be more apparent in dark or shaded areas, i.e., behind furniture and in closets.

CAUTIONS

APPLICATION:

Do not apply this product when surface is above 95°F.

Good painting practices dictate that all paint products be tested for adhesion, appearance, color, and compatibility prior to application. Protect all adjacent surfaces from splash, spill and over-spray during application.

Check your community's local VOC regulations before applying.

(continued)

628 ARO-PLATE II SG: INTERIOR/EXTERIOR FIRE RETARDANT, QUICK DRY SEMI-GLOSS ENAMEL

PERSONAL:

This product may be irritating to eyes and skin. Avoid contact with eyes and skin. In case of eye contact, flush with clean, warm water for at least fifteen minutes and call a physician immediately. Avoid breathing vapor or mist. Wash skin thoroughly after contact. **DO NOT TAKE INTERNALLY.** Keep out of reach of children and unqualified personnel. Consult the Material Safety Data Sheet for complete product safety information.

STORAGE:

Store protected, in unopened containers, for up to two years.

REGIONAL OFFICES:

CORPORATE OFFICE / SAN DIEGO:

6625 Miramar Road
San Diego, CA 92121
(858) 626-3600
(800) 477-9991
(858) 626-3651 FAX

LOS ANGELES:

(626) 396-1142
Architectural / Sales Division
(800) 826-9048
(626) 396-1827 FAX

ORANGE COUNTY / INLAND EMPIRE:

(714) 630-8040
Architectural / Sales Division
(714) 666-2342 FAX

FRESNO / CENTRAL VALLEY:

(559) 448-8088
(559) 448-8090 FAX

NORTHERN CALIFORNIA:

(916) 852-8082
(916) 852-8090 FAX

ARIZONA:

(602) 275-5444
(602) 244-2715 FAX

NEVADA / LAS VEGAS:

(702) 895-9800
(702) 895-7798 FAX

NEVADA / RENO:

916) 852-8082
(916) 682-6905 FAX

WARRANTIES

Frazee warrants that its products will conform and perform in accordance with the product specification sheets. Frazee also warrants its products to be free from defects in material and manufacturing.

Frazee's liability to the buyer or any third party for any losses or damages, shall not exceed beyond replacement cost, excluding freight and handling of material, proven to be defective. Frazee agrees to respond to claims of defective material, upon receipt of written notification and verification of product defects. Any claim must be made within five days of the discovery of the defect. In no event shall the seller be liable for any consequential or incidental damages or loss of profits.

Frazee is not liable for variation in environment, application, color, or changes in procedure, which may cause unsatisfactory results.

PHILOSOPHY

Since 1896, integrity has been the cornerstone of our business philosophy. Integrity, together with service and quality, are essential ingredients in every product Frazee manufactures.